

# Fast-Metal Minute Adhesive



with a high solids content, pasty  
very short pot life, fast-curing  
gap-filling, residual elasticity

WEICON Fast-Metal Minute Adhesive is ideal for repairs and bondings with larger bonding gaps or bigger tolerances. The gap filling properties make it suitable for rough and poorly fitting surfaces but also to fill in cracks, cavities and unlevelled surfaces.

Fast-Metal Minute Adhesive can be used on numerous materials such as metal, plastic, fibre reinforced materials, ceramics, glass, stone and wood.

ISSA: 75.629.51

IMPA: 81 29 81

## Technical data

Basis	epoxy resin
Nature	paste consistency, crack-filler
Supplied in	double syringe
Content	24 ml
Mixing ratio by volume (Resin/Hardener)	1 : 1
Pot life with 10 ml material at +20 °C	3-4 Min.
Density of the mixture	1,80 g/cm <sup>3</sup>
Viscosity of the mixture at +20 °C	300.000 mPa·s
Processing temperature	+10 bis +30 °C
Curing temperature	+6 bis +40 °C
Colour	grey
Gap covering power to max.	4 mm
Handling strength (35% strength/+20 °C) after	40 Min.
Capable of bearing mechanical loads(50% strength/+20 °C) after	2 h
Final strength (100% strength/+20 °C) after	1 day(s)
Pressure	10 MPa
Tensile	24 MPa
Torsion	58 MPa
Shore hardness D	70
Steel, sand-blasted	20 N/mm <sup>2</sup>
Aluminium, sand-blasted	19 N/mm <sup>2</sup>
Rigid PVC, roughened	11 N/mm <sup>2</sup>
Temperature resistance	-50 bis +145 °C

## Pretreatment of the surface

To ensure a perfect bond, the surfaces to be joined must be clean and dry (e.g., clean and degrease using WEICON Surface Cleaner). Smooth surfaces should be roughened, e.g. by sandblasting.

## Processing

Fast-Metal Minute Adhesive can be processed directly from the double cartridge. Reject the first centimetre of the dosed bead. Mix the product thoroughly. Apply adhesive mixture quickly to only one of the surfaces to be bonded. Join both surfaces immediately afterwards.

## Storage

When kept at a constant room temperature of about +20 °C and unopened in dry conditions, WEICON Epoxy Adhesives will keep for at least 18 months. Avoid direct sunlight. If these storage instructions are disregarded, the storage life will be reduced to six months.

Epoxy resins are fundamentally liable to crystallise at temperatures of less than +5 °C. This effect is accentuated by wide variations in temperature such as can frequently occur during transport in winter. This also has a negative effect on working qualities, curing and technical details, although these effects can be reversed by warming up to a maximum of +50 °C (no naked flame).

In the case of WEICON Epoxy Adhesives, careful selection and combination of the base resins (bisphenol A and F) ensures a reduction of crystallisation.

## Note

Any product specifications and recommendations given herein must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do warrant the continuously high quality of our products being free from defects in accordance with and subject to our General Sales Conditions. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

## Health and Safety

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster  
P.O. Box 84 60 · DE-48045 Münster  
Germany

Tel. +49 (0) 251 / 93 22-0  
Fax +49 (0) 251 / 93 22-244  
Fax +49 (0) 251 / 93 22-233 Export  
[www.weicon.de](http://www.weicon.de) · [info@weicon.de](mailto:info@weicon.de)

### WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216  
Dubai · U.A.E

Phone +971 4 880 25 05  
Fax +971 4 880 25 09  
Mobile +971 50 545 99 83  
[www.weicon.ae](http://www.weicon.ae) · [info@weicon.ae](mailto:info@weicon.ae)

### WEICON Inc.

20 Steckle Place · Unit 20  
Kitchener · Ontario · N2E 2C3  
Canada

Phone +1 519 896 5252  
Fax +1 519 896 5254  
Cell +1 519 590 5168  
[www.weicon.ca](http://www.weicon.ca) · [info@weicon.ca](mailto:info@weicon.ca)

### WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi  
Arifağa Sokak No: 29 Kat: 3  
34530 Yenibosna – İstanbul Turkey  
[www.weicon.biz.tr](http://www.weicon.biz.tr) · [info@weicon.biz.tr](mailto:info@weicon.biz.tr)

### WEICON Romania SRL

Str. Podului Nr.1  
547176 Budiu Mic (Targu Mures)  
[www.weicon.com](http://www.weicon.com) · [office@weicon.com](mailto:office@weicon.com)