

Rust Protection 2000 PLUS

Technical Datasheet

Create Date: 15.02.2016 - Page 1/1



special corrosion and weathering resistant surface coating

Rust Protection 2000 PLUS is a particularly corrosion and weather resistant surface coating on the basis of ferric oxide (hematite). The usage of highly-pure ferric oxide pigments in a fl aky arrangement achieves permanent, weather-resistant and water-repellent surface protection.

Metal parts coated with Rust Protection 2000 PLUS did not show any corrosion after more than 2000* hours in a salt spray test.

WEICON Rust Protection 2000 PLUS can be used on halls and steel structures, iron railing, lattice towers, fences, handrails, balcony grates, rolling gates, outdoor lights, and on points particularly susceptible to corrosion.

Technical data

i ecililicai uata	
Colour	charcoal-grey (DB 703) / silver-grey (DB 701)
Application	Indoors and outdoors
Binding agent	Acrylic resin
Pigment	Lamellar hematite
Pigment purity	> 90% ferric oxide
Percentage of metal in dry film	ca. 58 %
Content	400 ml
Specific weight	1,3 - 1,4 g/cm ³
Processing temperature +5	to +35, optimum temperature from +18 to + 25 $^{\circ}\text{C}$
Consumption at 1.5 cross coats	ca. 160 ml/m²
Layer thickness at 1.5 cross coat	ca. 60-80 µm
dust dry after	ca. 30 Min.
Hardened after	ca. 24 h
paintable	ca. 24 h
Abrasion-resistant	abrasion-resistant
Cross cutting DIN 53151 / ISO 2	Cross cut characteristic value GT 0 to
	GT 1
Salt spraying test ISO 9227	>2.000* h
Mandrel bend test DIN EN ISO 1	no hair cracking
Top coating	not required
Temperature resistance after cor	nplete hardening about -50 to +300 °C
Storage stability	24 months

^{*} applied in two cross-coated layers onto an undamaged zinc undercoat

Pretreatment of the surface

Clean and degrease surfaces with WEICON Cleaner S.

Processing

Clean and degrease surfaces, for example with Cleaner Spray S. Shake can before use. At room temperature (approx. +20°C), spray on two cross-coated layers of Rust Protection 2000 PLUS keeping a distance of 25 cm.

Consumption at 1 ½ cross - coated layers: 160 ml/m².

Storage

Pressurized container: protect from sunlight and do not expose to temperatures exceeding $+50\,^{\circ}$ C.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation.

We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Health and Safety

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster P.O. Box 84 60 · DE-48045 Münster Germany

Tel. +49 (0) 251 / 93 22-0 Fax +49 (0) 251 / 93 22-244 Fax +49 (0) 251 / 93 22-233 Export www.weicon.de · info@weicon.de

WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216 Dubai · U.A.E

Phone +971 4 880 25 05 Fax +971 4 880 25 09 Mobile +971 50 545 99 83 www.weicon.ae · info@weicon.ae

WEICON Inc.

20 Steckle Place · Unit 20 Kitchener · Ontario · N2E 2C3

Phone +1 519 896 5252 Fax +1 519 896 5254 Cell +1 519 590 5168 www.weicon.ca · info@weicon.ca

WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi Arifağa Sokak No: 29 Kat: 3 34530 Yenibosna – Istanbul Turkey www.weicon.biz.tr · info@weicon.biz.tr

WEICON Romania SRL

Str. Podului Nr.1 547176 Budiu Mic (Targu Mures) www.weicon.com · office@weicon.com