

# Primer E 500

Technical Datasheet

Create Date: 15.02.2016 - Page 1/1



for metal surfaces

Especially for silicone - for pre-treating non-absorbent surfaces such as aluminium, VA steel, brass, copper, zinc, tinplate and enamel, ceramic and glass as well as plastics such as ABS, PVC hard, PA6.6, GFC etc.

#### **Technical data**

Basis	Silicone resin, solvent-based
Colour	Slightly yellowish, transparent
Density	0,78 g/cm <sup>3</sup>
Consumption	100 ml
Working temperature	+10 to +25 °C
Evaporation time after application	approx. 60 min.
Adhesive application at the latest after	8 hours

#### Suitable for:

- WEICON Silicone A, F and N
- WEICON HT-300
- WEICON Black-Seal

#### Pretreatment of the surface

The surfaces to be treated must be dry, clean, and free of dust and grease (e.g. WEICON Surface Cleaner).

#### **Processing**

Shake well before use, then apply a thin layer with a clean cloth.

Recommended evaporation time:

Primer M 100: minimum 10 minutes, max. 24 hours Primer K 200: minimum 10 minutes, max. 24 hours Primer S 300: minimum 60 minutes, max. 4 hours Primer P 400: minimum 10 minutes, max. 1 hour Primer E 500: minimum 60 minutes, max. 8 hours

The following bonding process should be done within the time period mentioned above. Please respect the minimum evaporation time. After a longer storage time or soilings in the meantime, clean again the bonding surfaces and apply again the primer. For unknown material types it is necessary to test suitability and compatibility.

## Storage

Keep away from sources of ignition - No smoking. The heavy vapours may bridge a long distance to source of ignition.

Vapours can form an explosive mixture with air. Highly volatile,

flammable components are released in processing. Take precautionary measures against static discharges. Prevent penetration into the ground. Do not store together with food.

Store closed container at cool and aired place. Protect from heat and direct solar radiation. Store in a dry place. Protect from heat/overheating.

When unopened and stored in a normal climate ( $+23^{\circ}$ C and 50 % rel. humidity), WEICON Primer have a shelf life of 9 - 12 months, depending on the type.

#### Note

Any product specifications and recommendations given herein must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do warrant the continuously high quality of our products being free from defects in accordance with and subject to our General Sales Conditions. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

#### **Health and Safety**

When using WEICON products, the physical, safety technical, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

# WEICON GmbH & Co. KG (Headquarter)

Königsberger Str. 255 · DE-48157 Münster P.O. Box 84 60 · DE-48045 Münster Germany

Tel. +49 (0) 251 / 93 22-0 Fax +49 (0) 251 / 93 22-244 Fax +49 (0) 251 / 93 22-233 Export www.weicon.de · info@weicon.de

### WEICON Middle East L.L.C.

Jebel Ali Ind Area 3 · P.O. Box 118 216 Dubai · U.A.E

Phone +971 4 880 25 05 Fax +971 4 880 25 09 Mobile +971 50 545 99 83 www.weicon.ae · info@weicon.ae

#### WEICON Inc.

20 Steckle Place · Unit 20 Kitchener · Ontario · N2E 2C3 Canada

Phone +1 519 896 5252 Fax +1 519 896 5254 Cell +1 519 590 5168 www.weicon.ca · info@weicon.ca

# WEICON Kimya Sanayi Tic. Ltd. Şti.

Yenibosna Mahallesi Yalçın Koreş Caddesi Arifağa Sokak No: 29 Kat: 3 34530 Yenibosna – Istanbul Turkey www.weicon.biz.tr · info@weicon.biz.tr

#### **WEICON Romania SRL**

Str. Podului Nr.1 547176 Budiu Mic (Targu Mures) www.weicon.com · office@weicon.com